



Characteristic

Thicker version of **9061** is a **multipurpose duct tape** considered as a universal product for **sealing, repairing, jointing** and **packaging** thanks to higher adhesion, holding power and tensile strength. Thanks to its water resistance, conformability to irregular surfaces and easy tear, 9061 is the perfect product for general interventions like **emergency repairs** and covers of materials that need flexibility, **protection** from **damages** and **temporary sealing** in high-tension conditions.


This adhesive tape is designed to be applied semi permanently without clean removal, can be used as **protection** and **sealant** in many contexts like home, construction sites, industrial interventions and even agricultural activities.

CHARACTERISTICS	UNITS	STD. VALUES	TOLER.	TEST METHOD
Total Weight	g/m ²	155	± 10%	ISO 536
Total Thickness	µm	175	± 10%	AFERA 5006
MD tensile strength	N/cm	> 32		AFERA 5004
MD elongation at break	%	> 10		AFERA 5004
Adhesion to steel plate	N/cm	> 7		AFERA 5001
Rolling ball tack	cm	< 0,5		PSTC 6

Available colours: SILVER - BLACK

Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice.

All information has to be intended as generic advise for the use of products. Users have to verify the suitability of each tape in actual application under specific conditions.



Terms & Conditions of liability

Fost tapes must be stored in a dry location, protected from direct sunlight exposure and from freezing. Storage temperatures should be as close as possible to room temperature; suggested storage temperature should range from 15 to 25°C with max. relative humidity of 60%.

Make sure the surface you wish to place the tape on is cleaned, dried and free from oil and dust. It is suggested not to apply the tape with temperatures lower than 10°C.

With a storage temperature lower than 10°C, it is always suggested temperature reconditioning of the tape at room temperature (15°C - 25 ° C) before its use.

Shelf life from date of manufacture: (no yellowing and < 10% loss in performance at 23 °C, 50 % humidity) is considered 12 months for Slit rolls and 6 for Jumbo rolls.

FOST does not take responsibility for the defective material is not stored and used in accordance with the conditions listed above.